



SPECIFICATION SHEET

MBT -Mercaptobenzothiazole. CAS 149-30-4

Specification:	96% min
Initial melting point:	171 deg.C min
Ash:	0.3% max
Loss on drying:	0.4% max
Percentage passing 100mesh:	99.9%
Appearance:	yellow or light yellow powder

Analysis batch # 0203181

Appearance	Light Yellow powder
Initial Melting Point	171.2 deg C
Loss on Drying	0.12%
Ash	0.21%
Percentage passing 100 mesh	0.04%

Packaging 25kg

The content of this specification is produced by RPL from information provided from its source. Whilst all care is taken, RPL does not warrant the accuracy of the information and the customer must satisfy itself as to the suitability of the goods for the customers purpose.

REV01 280306 ADDRESS DETAILS

**RPL TRADING PTY LTD • ABN 88 087 329 128 •
159-161 ALLINGHAM ST, GOLDEN SQUARE VIC 3555
8.30AM-5.00PM PHONE: 1300 132 134 • FAX: 1300 669 660
AH. 0417 15 38 31**